MULTI JET FUSION **PA 11 BLACK** Supplier's Material: HP 3D High Reusability PA 11



PRODUCT DESCRIPTION

PA 11 Black provides excellent ductility and temperature resistance without sacrificing tensile strength. It offers one of the highest elongation break thresholds in the nylon family. Final parts are water- and airproof without further treatment and possess more consistent mechanical properties when compared to processes like selective laser sintering.

APPLICATIONS

The material is suited for functional, moving parts with features like snap fits and living hinges. Its black colour makes it desirable for optical applications due to low reflectivity. The material can also be used to build housings, enclosures, and fixtures, as well as sport goods.



KEY PRODUCT BENEFITS

- High elongation at break
- Flexibility
- Uniform black colour

PROPERTIES

PROPERTY	TEST METHOD	VALUE
Colour	-	Black
Sintered Density*	ASTM D792	$1,05 \pm 0,01 \text{ g/cm}^3$
Suface Roughness**	DIN EN ISO 4287	Ra = 12-16 μm; Rz = 70-95 μm
E-Module (x-y plane)	DIN EN ISO 527, test speed 10 mm/min	$1800 \pm 200 \text{ MPa}$
E-Module (z plane)		$1800 \pm 200 \text{ MPa}$
Tensile strength (x-y plane)		$52 \pm 4 \text{ MPa}$
Tensile strength (z plane)		52 ± 4 MPa
Elongation at break (x-y plane)		36% ± 5%
Elongation at break (z plane)		$30\% \pm 5\%$
Heat deflection temperature @ 0,46 MPa*	ASTM D648 Test Method A	185 ± 5°C
Heat deflection temperature @ 1,82 MPa*		54 ± 5 ℃

TOLERANCES

*From supplier data sheet

For well-designed parts, tolerances of \pm 0.25mm plus 0.002mm/mm can typically be achieved. Note that tolerances may change depending on part geometry.

